

## Polycrystalline Mullite Composite Brick Furnace Refractory Brick For Glass Kilns

Our Product Introduction

for more products please visit us on [bricksrefractory.com](http://bricksrefractory.com)

### Basic Information

- Place of Origin: Zhengzhou, China
- Brand Name: Rongsheng Xinwei
- Certification: ISO9001
- Model Number: RSDJM-70
- Minimum Order Quantity: 1 Ton
- Price: 200-800 USD
- Packaging Details: Packed on wooden pallets, with water-proof cover, and tightened with plastic/steel bandages
- Delivery Time: 10-20 Days
- Payment Terms: TT; L/C
- Supply Ability: 2000 tons/month



### Product Specification

- Compressive Strength: High/Medium/Low
- Origin: China
- Refractoriness Under Load: Excellent
- Firing Temperature: High/Medium/Low
- Thermal Capacity: High
- Porosity: High, Medium, Low
- Strength: High
- Resistance To Spalling: Good
- Heat Capacity: High
- Thermal Conductivity: 0.15-0.8 W/m.K
- Feature: High Refractoriness
- Temperature: High
- Raw Material: High Alumina Content Bauxite
- Corrosion Resistance: High
- Softening Point: High



### More Images



### Product Description

#### Product Description of Polycrystalline Mullite Composite Brick Furnace Refractory Brick For Glass Kilns

Polycrystalline mullite composite brick is made of high-purity fused mullite, Australian zircon sand, slabcorundum, composite ultra fine powder and special additive by high-pressure forming and high-temperaturesintering.

It is mainly used in small furnace tongwe and other key parts of glass kiln. It has high temperature resistance.erosion resistance, high temperature corrosion resistance, good thermal shock stability and excellent creepresistance at high temperature.

Our Product Introduction

**Product Specification of Polycrystalline Mullite Composite Brick Furnace Refractory Brick For Glass Kilns**

| Item  | RSDJM-70 |
|---|----------|
| $\text{Al}_2\text{O}_3, \% \geq$              | 70       |
| $\text{SiO}_2, \% \leq$                       | 23       |
| $\text{ZrO}_2, \% \geq$                       | 6        |
| $\text{Fe}_2\text{O}_3, \% \leq$              | 0.2      |
| $\text{BD}, \text{g}/\text{cm}^3 \geq$        | 2.95     |
| $\text{AP}, \% \leq$                          | 13       |
| $\text{CCS}, \text{MPa} \geq$                 | 120      |
| $0.2\text{MPa RUL}, \geq$                     | 1700     |
| Creep Rate 1200 x50h, $\% \leq$               | 0.5      |
| $\text{TSR}(1100, \text{Water Cooling}) \geq$ | 15       |

**Henan Rongsheng Xinwei New Materials Research Institute Co., Ltd**

+86-18538509097



Jackyhan2023@outlook.com

[bricksrefractory.com](http://bricksrefractory.com)

11th Floors, Building 6, China Central Electronic Commerce Port, Daxue Road, Zhengzhou, Henan, China