


550mm To 750mm Large-Diameter RP, HP, And UHP Grades Graphite Electrodes For EAF

Our Product Introduction

for more products please visit us on bricksrefractory.com

Basic Information

- Place of Origin: Zhengzhou ,China
- Brand Name: Rongsheng Xinwei
- Certification: ISO9001
- Model Number: UP HP UHP
- Minimum Order Quantity: 1 Ton
- Price: 200-800USD
- Packaging Details: Packed on wooden pallets, with water-proof cover, and tightened with plastic/steel bandages
- Delivery Time: 10-20 Days
- Payment Terms: TT; L/C
- Supply Ability: 2000tons /month



Product Specification

- Highlight: EAF Graphite Electrodes ,
UHP Graphite Electrodes ,
750mm Graphite Electrodes

Product Description

Product Overview of 550mm to 750mm Large-Diameter RP, HP, And UHP Grades Graphite Electrodes For EAF

Introducing our large-diameter Carbon Graphite Electrodes, available in sizes of 550mm, 650mm, 700mm, and 750mm. Designed for high-performance in electric arc furnaces, these electrodes are crafted from superior-quality carbon graphite, ensuring exceptional conductivity and durability.

Our Product Introduction



Key Features of RP, HP, And UHP Grades Graphite Electrodes For EAF

High Electrical Conductivity: Our electrodes are engineered to facilitate efficient energy transfer, maximizing the melting process in electric arc furnaces.

Thermal Resistance: Designed to withstand extreme temperatures, these electrodes maintain their performance even under the most demanding conditions.

Robust Durability: Constructed from high-grade materials, they exhibit excellent resistance to oxidation and wear, providing a longer lifespan.

Custom Sizes Available: With a range of diameters, we can meet your specific application needs.

Applications of RP, HP, And UHP Grades Graphite Electrodes For EAF

These oversized electrodes are ideal for various applications, including:

Electric Arc Furnaces: Essential for the production of steel and recycling metals.

Foundries: Suitable for non-ferrous metal processing.

Silicon Production: Critical for chemical manufacturing processes.

Technical Parameter of Graphite Electrodes and Nipple:

Regular Graphite Electrode

Item		Nominal diameter mm							
		75~130		150~225		250~300		350~450	
Grade		Excellent	—	Ex	—	Ex	—	Ex	—
Resistivity $\mu\Omega\cdot m \leq$	Electrode	8.5	10.0	9.0	10.5	9.0	10.5	9.0	10.5
	Connector	8.0		8.0		8.0		8.0	
Flexural strength MPa \geq	Electrode	10.0		10.0		8.0		7.0	
	Connector	15.0		15.0		15.0		15.0	
Elastic Modulus GPa \leq	Electrode	9.3		9.3		9.3		9.3	
	Connector	14.0		14.0		14.0		14.0	
Bulk density g/cm ³ \geq	Electrode	1.58		1.53		1.53		1.53	
	Connector	1.70		1.70		1.70		1.70	
Thermal expansion coefficient 10-6/ room temperature ~600 \geq	Electrode	2.9		2.9		2.9		2.9	
	Connector	2.7		2.7		2.8		2.8	
Ash % \leq		0.5		0.5		0.5		0.5	

High Power Graphite Electrodes

Item		Nominal diameter mm	
		200~400	450~500
Resistivity $\mu\Omega\cdot m \leq$	Electrode	7.0	7.5
	Connector	6.3	6.3
Flexural strength MPa \geq	Electrode	10.5	10.0
	Connector	17.0	17.0
Elastic Modulus GPa \leq	Electrode	14.0	14.0
	Connector	16.0	16.0
Bulk density g/cm ³ \geq	Electrode	1.60	1.60
	Connector	1.72	1.72
Thermal expansion coefficient 10-6/ Room temperature~600 \geq	Electrode	2.4	2.4
	Connector	2.2	2.2
Ash % \leq		0.5	0.5

Ultra High Power Graphite Electrode

Item		Nominal diameter mm		
		300~400	450~500	550~650
Resistivity $\mu\Omega\cdot m \leq$	Electrode	6.2	6.3	6.0
	Connector	5.3	5.3	4.5
Flexural strength MPa \geq	Electrode	10.5	10.5	10.0
	Connector	20.0	20.0	22.0

Elastic Modulus GPa ≤	Electrode	14.0	14.0	1.66
	Connector	20.0	20.0	1.78
Bulk density g/cm3 ≥	Electrode	1.67	1.66	1.66
	Connector	1.74	1.75	1.78
Thermal expansion coefficient 10-6/ Room temperature~600 ≥	Electrode	1.5	1.5	1.5
	Connector	1.4	1.4	1.3
Ash % ≤		0.5	0.5	0.5

Quality Assurance
We maintain strict quality control throughout the manufacturing process to ensure that every batch meets international standards. With over 20 years of industry experience, we are committed to delivering reliable and high-performance products.

Why Choose Rongsheng RP, HP, And UHP Grades Graphite Electrodes For EAF?
Industry Leadership: With decades of experience, we have established ourselves as a top supplier of refractory materials.
Global Presence: Our products are exported to over 100 countries, reinforcing our reputation as a trusted provider.
Customer-Centric Approach: We offer tailored solutions and responsive support to meet your specific requirements.

Contact Us
For more information or to place an order, please reach out to us:
Tel/Whatsapp: +86-18538509097
Email: Jackyhan2023@outlook.com
Experience the quality and performance of our oversized Carbon Graphite Electrodes and elevate your production processes today!

 **Henan Rongsheng Xinwei New Materials Research Institute Co., Ltd**

 +86-18538509097  Jackyhan2023@outlook.com  bricksrefractory.com

11th Floors, Building 6, China Central Electronic Commerce Port, Daxue Road, Zhengzhou, Henan, China