

High Purity Alumina Ceramic Balls High Alumina Ball For Iron Steel Industry

Our Product Introduction

for more products please visit us on bricksrefractory.com

Basic Information

- Place of Origin: Zhengzhou ,China
- Brand Name: Rongsheng Xinwei
- Certification: ISO9001
- Model Number: RS-65, RS-70, RS-75, RS-95
- Minimum Order Quantity: 1 Ton
- Price: 200-800USD
- Packaging Details: packed on wooden pallets, with water-proof cover, and tightened with plastic/steel bandages
- Delivery Time: 20-30DAYS
- Payment Terms: TT; L/C
- Supply Ability: 2000tons /month



Product Specification

- Bulk Density: High
- Chemical Resistance: High
- Cold Crushing Strength: High
- Color: White
- Density: High
- Material: High Alumina
- Porosity: Low
- Refractoriness: High
- Refractoriness Under Load: High
- Shape: Brick
- Size: Standard
- Softening Point: High
- Thermal Conductivity: Low
- Thermal Shock Resistance: High
- Highlight: **High Purity Alumina Ceramic Balls,**



Our Product Introduction

Product Description

High Purity Alumina Ceramic Balls High Alumina Refractory Brick For Iron & Steel Industry

Product Description of High Purity Alumina Ceramic Balls

Refractory Alumina Ceramic Balls are made of industrial alumina and refractory kaolin as the main raw materials, which are made by scientific formula, forming and hightemperature calcination.

Refractory ball is divided into ordinary refractory ball and high aluminum resistance ball. Refractory porcelain ball high temperature resistance to high temperature can reach 1900 degrees, high mechanical strength and long-term use.

GOOD HEAT STORAGE EFFECT/ GOOD CHEMICAL STABILITY

1.Free sample 2.Custom specifications 3.Good service



Features of High Purity Alumina Ceramic Balls

1. high temperature resistant performance, the highest heat resistant ceramic ball temperature can reach 1900 degrees;
2. high mechanical strength, long use cycle;
3. good chemical stability, no chemical reaction with the material;
4. good thermal stability, high strength;

High Alumina Refractory Ball Applications

High alumina ball application in chemical fertilizer plant of high and low temperature transformation furnace, reformer, hydrogenation, desulfurization tank and methanation furnace, dispersed liquid, and supporting, covering and protecting catalyst role, can also be used in heating furnace of iron and steel industry and the transformation of equipment, ordinary refractory ball suitable for sulfuric acid and fertilizer industries converter and transform furnace, high aluminum refractory ball is suitable for industries such as steel, urea, hot blast furnace, heating and transformation furnace and other equipment.

Product Parameter of High Purity Alumina Ceramic Balls

Item	High alumina	Low creep	Mullite	
Size(mm)	40-80	40-80	40-80	
AL ₂ O ₃ (%)	65	70	75	
Refractoriness under load(°C)	1450	1460	1530	
Apparent Porosity(%)	25	23	22	
Bulk Density(g/cm ³)	2.3	2.4	2.5	
Cold crushing strength(Mpa)	13	14	32	
Thermal shock resistance (1100°Cwater cooling) cycle ≥	15	10	20	
Refractoriness(°C)	1710	1750	1800	



Henan Rongsheng Xinwei New Materials Research Institute Co., Ltd



+86-18538509097



Jackyhan2023@outlook.com



bricksrefractory.com

11th Floors, Building 6, China Central Electronic Commerce Port, Daxue Road, Zhengzhou, Henan, China