

## Fan Shaped High Alumina Refractory Brick High Alumina Curved Brick For Hot Blast Stove Roof

Our Product Introduction

for more products please visit us on [bricksrefractory.com](http://bricksrefractory.com)

### Basic Information

- Place of Origin: Zhengzhou ,China
- Brand Name: Rongsheng Xinwei
- Certification: ISO9001
- Model Number: RS-48, RS-55, RS-65, RS-75, RS-80
- Minimum Order Quantity: 1 Ton
- Price: 200-800USD
- Packaging Details: packed on wooden pallets, with water-proof cover, and tightened with plastic/steel bandages
- Delivery Time: 20-30DAYS
- Payment Terms: TT; L/C
- Supply Ability: 2000tons /month



### Product Specification

- Al<sub>2</sub>O<sub>3</sub> Content: Above 48%
- Application Field: Cement Kiln, Glass Kiln, Metallurgical Furnace
- Application Temperature: Above 1500
- Bulk Density: Above 2.2g/cm<sup>3</sup>
- Cold Crushing Strength: Above 70MPa
- Color: Red
- Fe<sub>2</sub>O<sub>3</sub> Content: Below 1.5%
- Material: High Alumina Refractory Brick
- Package: Carton Box
- Porosity: Below 18%
- Refractoriness: Above 1790
- Shape: Square
- Size: 230x114x65mm
- Thermal Conductivity: Below 0.8W/m.K

### Product Description

#### Product Description of Customized Special Shapes Fan-shaped High-alumina Brick High Alumina Curved Brick For Hot Blast Stove Roof

High alumina bricks refer to aluminosilicate refractory products with aluminum oxide (Al<sub>2</sub>O<sub>3</sub>) content higher than 48%. It belongs to neutral refractory material. It is formed by shaping and calcining bauxite or other raw materials with high alumina content. High thermal stability and fire resistance above 1770 . It has good slag resistance and is used for lining steel making electric furnace, glass furnace, cement rotary furnace, etc.

High load soft and low creep high alumina brick is a high-grade refractory material made of special grade bauxite, fused corundum and fused mullite. The product has the advantages of small high-temperature creep, strong corrosion resistance, good thermal shock stability, etc. It is suitable for large and medium-sized hot blast furnaces.

Our Product Introduction



#### Advantage of High Alumina Curved Brick For Hot Blast Stove Roof

1. High refractoriness;
2. High temperature strength;
3. High thermal stability;
4. Neutral refractory;
5. Good resistance to acid and basic slag corrosion;
6. High refractoriness under load;
7. High temperature creep resistance;
8. Low apparent porosity;

#### Application of high alumina bricks

As a basic material in the field of high-temperature technology, high alumina bricks are widely used in cement, glass building materials, steel smelting, petrochemical and other industries. High temperature industrial furnaces for high alumina bricks include blast furnace, hot blast furnace, electric furnace, blast furnace, reverberatory furnace and rotary kiln lining. In addition, high alumina bricks can also be processed into open hearth regenerative grid bricks, socket bricks for pouring system, nozzle bricks, etc. according to the requirements of industrial furnaces.

#### Product Specification of Special Shapes Fan-shaped High-alumina Brick

Item		Properties			
		RS-80	RS-75	RS-65	RS-55
Al <sub>2</sub> O <sub>3</sub> (%)		80	≥75	≥65	≥55
Refractoriness (°C)		≥1790	≥1790	≥1790	≥1770
Bulk density (g/cm <sup>3</sup> )		2.65	2.5	2.45	2.4
Softening temperature under load (°C)		1530	≥1520	≥1500	≥1470
Linear changes on reheating (%)	1500°CX2H	0.1	0.1	0.1	0.1
		-0.4	-0.4	-0.4	-0.4
	1450°CX2H				
Apparent porosity (%)		22	≤23	≤23	≤22
Cold crushing strength (Mpa)		55	≥50	≥45	≥40



**Henan Rongsheng Xinwei New Materials Research Institute Co., Ltd**



+86-18538509097



Jackyhan2023@outlook.com



[bricksrefractory.com](http://bricksrefractory.com)

11th Floors, Building 6, China Central Electronic Commerce Port, Daxue Road, Zhengzhou, Henan, China