Yellow Refractory Fire Clay Brick 30-48% Alumina For Glass Furnace

Basic Information

Place of Origin: Zhengzhou ,ChinaBrand Name: Rongsheng Xinwei

• Certification: ISO9001

• Model Number: SK-30, SK-32, SK-34, SK-35

• Minimum Order Quantity: 1 Ton

• Price: 200-800 USD

• Packaging Details: packed on wooden pallets, with water-proof

cover, and tightened with plastic/steel bandages

Delivery Time: 10-20 Days
Payment Terms: TT; L/C
Supply Ability: 2000 tons/month



Product Specification

• Chemical Resistance: Yellow · Color: • Compressive Strength: High Density: High Durability: High • Fire Resistance: High • Frost Resistance: High Material: Clay Refractoriness: High Shape: Rectangular • Size: Standard Surface: Smooth Texture: Fine • Thermal Conductivity: Low . Water Absorption: Low



More Images





Product Description

Description of Rongsheng High Quality Fireclay Bricks Yellow Furnace Refractory Bricks With 30-48% Alumina For Glass Furnace

Fireclay brick is manufactured in accordance with the latest national standards using high-quality local fireclay materials. It has a uniform bulk density, high strength, low thermal conductivity, and low impurity. The refractoriness is up to 1690-1730 degrees Celsius. Fireclay refractory brick is widely used and is the most produced type of refractory brick.



Product Features of Rongsheng High Quality Fireclay Bricks

High refractoriness Good mechanical strength Low thermal conductivity Chemical resistance High Durability

Product Application of Furnace Refractory Fireclay Bricks With 30-48% Alumina For Glass Furnace
Fireclay brick is widely used in a variety of industrial applications, including metallurgy, building materials, the chemical
industry, and petroleum machinery manufacturing. It is used in a wide range of equipment, including heating furnaces, soaking pits, heat treatment furnaces, blast furnaces, hot blast furnaces, coke ovens, tunnel kilns, rotary kilns, torpedo cars, chemical reactors, incinerators, metal furnaces, glass furnaces, and flues.

Product Specification of High Quality Refractory Fireclay Bricks

Alumina contents range from 30% to 48%				
Material	fire clay material			
	earthy yellow			
Size	Standard sizing: 230 x 114 x 65 mm ,Special size and OEM Service also provide!			
Shape	Straight Brick,special-shaped brick,checher brick,trapezoidal brick,Bricks with taper,arch brick,skew brick,ect.			

Fine also devials						High alum	ina bria
Item/Grade	Fire clay brick						
1.0.11/ 0.1.000	SK-30	SK-32	SK-34	SK-35	SK-36	SK-37	SK-
AL2O3% (≥)	30	35	38	45	55	65	7(
Fe2O3% (≤)	2.5	2.5	2	2	2	2	2
Refractoriness(SK)	30	32	34	35	36	37	38
Refractoriness under load, 0.2 MPa, °C (≥)	1250	1300	1360	1420	1450	1480	150
Apparent porosity (%)	22-26	20-24	20-22	18-20	20-23	20-23	20-
Bulk density (g/cm³)	1.9-2.0	1.95-2.1	2.1-2.2	2.15-2.22	2.25-2.4	2.3-2.5	2.4-
Cold crushing strength ,MPa (≥)	20	25	30	40	45	50	60

Henan Rongsheng Xinwei New Materials Research Institute Co., Ltd





11th Floors, Building 6, China Central Electronic Commerce Port, Daxue Road, Zhengzhou, Henan, China