

Product Code	Chemical Composition (Mass Fraction),%					Bulk Density g/cm'	Water Absorpti
	Al2O3	Fe2O3	TiO2	CaO+MgO	K2O+Na2O		

GL-90	≥89.5	≤1.5	≤4.0	≤0.35	≤0.35	≥3.35		≤2.5
GL-88BA	≥87.5	≤1.6	≤4.0	≤0.4	≤0.4	≥3.20		≤3.0
GL-88B	≥87.5	≤2.0	≤4.0	≤0.4	≤0.4	≥3.25		≤3.0
GL-85A	≥85	≤1.8	≤4.0	≤0.4	≤0.4	≥3.10		≤3.0
GL-85B	≥85	≤2.0	≤4.5	≤0.4	≤0.4	≥2.90		≤5.0
GL-80	>80	≤2.0	≤4.0	≤0.5	≤0.5	≥2.90		≤5.0
GL-70	70~80	≤2.0	—	≤0.6	≤0.6	≥2.75		≤5.0
GL-60	60~70	≤2.0	—	≤0.6	≤0.6	≥2.65		≤5.0
GL-50	50~60	≤2.5	—	≤0.6	≤0.6	≥2.55		≤5.0



Henan Rongsheng Xinwei New Materials Research Institute Co., Ltd



+86-18538509097



Jackyhan2023@outlook.com



[bricksrefractory.com](http://bricksrefractory.com)

11th Floors, Building 6, China Central Electronic Commerce Port, Daxue Road, Zhengzhou, Henan, China