


Refractory Ceramic Balls 65% 92% 99% Al₂O₃ Alumina Ceramic Heat Storage Refractory Ball For Industry Furnace

Our Product Introduction

for more products please visit us on bricksrefractory.com

Basic Information

- Place of Origin: Zhengzhou ,China
- Brand Name: Rongsheng Xinwei
- Certification: ISO9001
- Model Number: RS-65, RS-70, RS-75, RS-95
- Minimum Order Quantity: 1 Ton
- Price: 200-800USD
- Packaging Details: packed on wooden pallets, with water-proof cover, and tightened with plastic/steel bandages
- Delivery Time: 20-30DAYS
- Payment Terms: TT; L/C
- Supply Ability: 2000tons /month




Product Specification

- Application: High Temperature Furnace
- Chemical Resistance: Good
- Color: Red
- Compressive Strength: High
- Corrosion Resistance: Good
- Density: High
- Material: High Alumina Refractory Brick
- Porosity: Low
- Refractoriness: High
- Shape: Rectangular
- Size: Standard
- Surface: Smooth
- Thermal Conductivity: Low
- Thermal Expansion: Low
- Thermal Shock Resistance: Good



More Images



Product Description

Product Description of Refractory Ceramic Balls 65% 92% 99% Al₂O₃ Alumina Ceramic Heat Storage Refractory Ball For Industry Furnace

Refractory balls are made of industrial alumina and refractory kaolin as the main raw materials, which are made by scientific formula, forming and hightemperature calcination.

Refractory ball is divided into ordinary refractory ball and high aluminum resistance ball. Refractory porcelain ball high temperature resistance to high temperature can reach 1900 degrees, high mechanical strength and long-term use.

Our Product Introduction



Product Features of High Alumina Refractory Ball

1. high temperature resistant performance, the highest heat resistant ceramic ball temperature can reach 1900 degrees;
2. high mechanical strength, long use cycle;
3. good chemical stability, no chemical reaction with the material;
4. good thermal stability, high strength;

Applications of High Alumina Refractory Ball

High alumina ball application in chemical fertilizer plant of high and low temperature transformation furnace, reformer, hydrogenation, desulfurization tank and methanation furnace, dispersed liquid, and supporting, covering and protecting catalyst role, can also be used in heating furnace of iron and steel industry and the transformation of equipment, ordinary refractory ball suitable for sulfuric acid and fertilizer industries converter and transform furnace, high aluminum refractory ball is suitable for industries such as steel, urea, hot blast furnace, heating and transformation furnace and other equipment.

Product Specification of High Alumina Refractory Ball

Item	High alumina	Low creep	Mullite	
Size(mm)	40-80	40-80	40-80	
AL ₂ O ₃ (%)	65	70	75	
Refractoriness under load(°C)	1450	1460	1530	
Apparent Porosity(%)	25	23	22	
Bulk Density(g/cm ³)	2.3	2.4	2.5	
Cold crushing strength(Mpa)	13	14	32	
Thermal shock resistance (1100°C water cooling) cycle ≥	15	10	20	
Refractoriness(°C)	1710	1750	1800	



Henan Rongsheng Xinwei New Materials Research Institute Co., Ltd



+86-18538509097



Jackyhan2023@outlook.com



bricksrefractory.com

11th Floors, Building 6, China Central Electronic Commerce Port, Daxue Road, Zhengzhou, Henan, China